

Halide-Driven Synthetic Control of InSb Colloidal Quantum Dots Enables Short-Wave Infrared Photodetectors

Muhammad Imran^{1,5}, Dongsun Choi^{1,5}, Darshan H. Parmar¹, Benjamin Rehl¹, Yangning Zhang¹, Ozan Atan¹, Gahyeon Kim^{1,2}, Pan Xia¹, Joao M. Pina¹, Mengsha Li³, Yanjiang Liu^{1,3}, Oleksandr Voznyy⁴, Sjoerd Hoogland¹, Edward H. Sargent^{1*}

¹Department of Electrical and Computer Engineering, University of Toronto, 10 King's College Road, Toronto, Ontario, M5S 3G4, Canada.

²Department of Chemistry, Korea University, Seoul, 02841, Republic of Korea

³Department of Materials Science and Engineering, University of Toronto, 184 College Street, Toronto, Ontario, M5S 3E4, Canada.

⁴Department of Chemistry, University of Toronto, 80 St. George Street, Toronto, Ontario, M5S 3H6 Canada

⁵These authors contributed equally to this work.

*E-mail: ted.sargent@utoronto.ca

Keywords: Colloidal quantum dots, indium antimonide, short wave-infrared, photodetector, group III-V semiconductors.

Abstract

In the III-V family of colloidal quantum dot (CQDs) semiconductors, InSb promises access to a wider range of infrared wavelengths compared to many light-sensing material candidates. However, achieving the necessary size, size-dispersity, and optical properties has been challenging. Here we investigate the synthetic challenges associated with InSb CQDs and find that uncontrolled reduction of the antimony precursor hampers the controlled growth of CQDs. To overcome this, we develop a synthetic strategy that combines non-pyrophoric precursors with zinc halide additives. Our experimental and computational studies show that zinc halide additives decelerate the reduction of the antimony precursor, facilitating the growth of more uniformly-sized CQDs. We also find that the halide choice provides additional control over the strength of this effect. The resultant CQDs exhibit

This article has been accepted for publication and undergone full peer review but has not been through the copyediting, typesetting, pagination and proofreading process, which may lead to differences between this version and the [Version of Record](#). Please cite this article as [doi: 10.1002/adma.202306147](https://doi.org/10.1002/adma.202306147).

This article is protected by copyright. All rights reserved.

well-defined excitonic transitions in spectral range of 1.26 eV to 0.98 eV, along with strong photoluminescence. By implementing a post-synthesis ligand exchange, we achieve colloiddally stable inks enabling the fabrication of high-quality CQD films. We present the first demonstration of InSb CQD photodetectors reaching 75% external quantum efficiency (QE) at 1200 nm, to our knowledge the highest SWIR QE reported among heavy-metal-free infrared CQD-based devices.

Introduction

Infrared (IR) photodetectors enable autonomous driving, augmented reality, biological sensing, and computer vision via light detection and ranging (LiDAR), and hyperspectral imaging technologies.[1] The limited availability of affordable and non-toxic IR active materials hinders their widespread use in this quickly developing consumer electronics market. The III-V semiconductor materials can address some of the prerequisites of high-performance photodetectors, but they face challenges in terms of cost, scalability, and substrate integration. Recent advancements in metamorphic buffers have improved the integration of III-V materials with silicon readout circuits; nevertheless, monolithic integration of III-Vs with silicon remains an ongoing area requiring further maturation.[2]

Colloidal quantum dots (CQD) are a promising low-cost material platform for IR photodetectors. Low-temperature solution processing allows facile integration with silicon and flexible substrates.[3] The quantum confinement of CQD provides an additional advantage of wavelength selectivity and tunability at the material level, reducing the complexity of device structures such as light filtering. PbS and InAs CQD, in particular, are actively investigated for IR light detection applications. Although PbS CQD offer favorable optoelectronic properties and have a well-established material and chemical foundation, their application in consumer products is limited due to their high toxicity, resulting in strict regulation.[4] Similarly, tuning the size of InAs CQDs using less toxic, commercially available precursors is challenging.[5]

InSb CQD represent an IR-active materials system of considerable potential interest: it is a direct bandgap semiconductor characterized by a bandgap energy of 0.17 eV at 300 K. The small electron and hole effective masses results in a large exciton Bohr radius of 60 nm. This facilitates greater size-tuning of the bandgap across a significant infrared spectral range, while also preserving quantum confinement effects.

InSb CQD synthesis, though, is challenging and rarely employed as it typically requires pyrophoric and unstable custom antimony precursors.[6] Attempts to synthesize these CQD using more stable antimony precursors, such as tris(dimethylamido)antimony and SbCl_3 , have resulted in colloidal dispersions but exhibited worse excitonic absorption features with broad photoluminescence (PL) linewidths.[7-9] Therefore, the development of synthetic strategies that facilitate precise control over the growth of InSb CQD while utilizing stable precursors has become increasingly imperative.

In this study, we developed a synthesis method utilizing a halide-based additive (zinc halides) to achieve superior control over the size distribution of InSb CQD. Density functional theory together with experimental results reveal that the addition of the Zn halides saturates the reaction environment and effectively reduces the rate of antimony precursor reduction. These two effects lead to the slow-down of the reaction between the In and Sb precursors that results in the formation of nearly monodispersed CQD, as confirmed by high angle annular dark field scanning transmission electron microscopy (HAADF-STEM). Analysis of optical absorption and transient absorption (TA) spectroscopy reveals well-defined excitonic transitions and strong PL at the band edge, offering tunable optical band gaps from 1.26 eV to 0.98 eV. We replaced the long aliphatic ligands with smaller halide-based ligands in a two-phase solution-exchange process. This led to an enhancement of the carrier mobility of the CQD in film. We integrated the ligand-exchanged CQD into solid-state films to create functional infrared photodetectors. We report the first demonstration of InSb CQD based photodetectors with external quantum efficiency reaching ~75% at 1200 nm with -1V bias, exceeding all reported heavy metal-free CQD-based IR photodetectors (see supplementary table 1).

Results and discussion

The synthesis of InSb CQD is completed in a two-step sequence. First, InCl_3 and SbCl_3 precursors are solubilized separately in oleylamine (OLA). In the second step, SbCl_3 -OLA precursor is injected into InCl_3 -OLA solution, followed by an injection of the reducing agent, *tert*-butylamine (DMEDA). Full details of the synthesis method can be found in the Materials and Methods section, and Figure S1.




Figure 1. Influence of ZnX_2 on growth of InSb CQD. (a) Optical absorption spectra InSb CQD samples prepared with and without different ZnX_2 salts in solution. (b) PXRD patterns of corresponding CQD samples recorded by drop casting the samples on silicon substrate. (c) Reduction rate of SbCl_3 upon DMEDA injection without and with ZnX_2 . (d) DFT simulations of SbCl_3 and DMEDA interaction, (e) formation of an adduct, with Al lone pair approaching the Cladduct with DMEDA, (f) reduced form of SbHCl_2 and transfer of Cl to Al, (e) ZnCl_2 adduct with DMEDA (some of the coordinating amines are not shown for clarity).

The InSb QD sample shows featureless absorption with a long tail at higher wavelength and no emission (Figure 1a). Powder X-ray diffraction (PXRD) of the CQD evidence the formation of phase-pure zinc blende InSb CQD (Figures S2). We attempted to improve size uniformity of the CQD by replacing InCl_3 with InCl . Previous studies on InAs CQD showed that the InCl in the reaction environment helped with size control.[10] But the synthesis of the InSb CQD using InCl precursor shows featureless optical absorption suggesting no control on the nucleation and growth of the CQDs (Figure S3).

Previous studies on nanocrystals synthesis show that the presence of zinc halides in the reaction environment affect the growth kinetic in various ways including some degree of size control and improve luminescence.[11-14] This motivated us to explore zinc halides as an additive during

nucleation and growth of InSb CQD to achieve better monodispersity. Specifically, in our synthetic system, we mixed zinc halide salts with InCl₃ and dissolved them in oleylamine followed by sequential injection of SbCl₃-OLA and DMEDA. The InSb materials prepared with ZnCl₂ exhibited featureless absorption but strong PL appeared (Figures 1a and S4). This inspired us to explore further the effects of other ZnX₂ salts (X = F, Br, and I). We varied the zinc halides while keeping all other reaction conditions constant (Figures 1a and S4). The samples prepared using ZnF₂ show a featureless absorption spectrum similar to ZnCl₂. In contrast, the samples prepared using ZnBr₂ and ZnI₂ exhibit sharper excitonic features and strong luminescence with narrow emission linewidths (Figures 1a and S4). PXRD analysis evidence the formation of phase-pure material across all the CQD samples (Figure 1b). HAADF-STEM analysis of CQD synthesized with ZnF₂ and ZnCl₂ reveals asymmetrical CQD with broad size distributions (Figure S5). On the other hand, CQD prepared using ZnBr₂ and ZnI₂ shows nearly uniform and symmetrical shaped CQDs (Figure S5).

In InAs synthesis, ZnX₂ were introduced as a way to activate the tris(dimethylamido)arsine precursor, which would not nucleate the CQD otherwise.[15, 16] Notably, in our synthesis, as well as in previous work employing different reducing agents, the CQDs easily nucleate even without halide additives.[9] However, the exact role of Zn halides in the synthesis has so far been unclear.[17] We thus turned to DFT modeling to explore the zinc halide effect (see details in Methods).

Our initial hypothesis was that additional halides provided by Zn or even Zn halide itself can coordinate to Sb and sterically protect it from interacting with DMEDA, and that Br could provide better protection than Cl. DFT simulations revealed, however, that neither the number nor the identity of the halide can prevent the reduction of the Sb halide by AlH₃, which is not just thermodynamically favorable but is also barrierless (we note that including the explicit solvent molecules was critical for facilitating the reduction process) (Figure 1d-f). Similarly, the formation of the SbCl₃-ZnCl₂ adduct was found to be favorable by only 0.1 eV, insufficient to keep it stable at room temperature, and even in the adduct form providing no additional steric protection against DMEDA.

We noted that ZnCl₂ forms a stable adduct with AlH₃ similar to SbCl₃ (both formation energies ~0.8 eV) (Figure 1d, e). However, unlike Sb, Zn does not get reduced, consistent with its higher redox potential. These results suggest that the injected excess ZnCl₂ coordinates to the freely available DMEDA, limiting its access and reactivity with SbCl₃. Yet again, DFT adduct formation energies show nearly no difference between ZnCl₂ and ZnBr₂.

To explain the effect of Cl vs. Br one thus needs to turn to their other potential differences. We hypothesized that one such difference could be their solubility in OLA. A less soluble product would need a complexation with DMEDA in order to get solubilized, thus scavenging it more efficiently. Testing this hypothesis with DFT remains unfeasible because to properly capture the weak van der Waals interactions with the long-chain ligands one cannot revert to short-chain amine analogous,

substantially increasing the size of the simulation box. Nevertheless, experimental test of ZnX_2 solubility in OLA under identical conditions confirmed that ZnCl_2 is 1.8 times more soluble than ZnBr_2 . Moreover, addition of DMEDA improved ZnBr_2 solubility, confirming the formation of ZnBr_2 -DMEDA adduct.

To validate our hypothesis that Zn halide inhibits the reduction of SbCl_3 , we investigated the reduction rate of SbCl_3 precursor alone with and without ZnX_2 precursors. All control experiments were performed by fully dissolving SbCl_3 precursor in OLA under nitrogen environment. The injection of DMEDA into SbCl_3 -OLA instantly turns the solution black suggesting the immediate Sb reduction. Similar rate of reduction for SbCl_3 was observed when ZnCl_2 was added to the solution. Contrary to this, the presence of ZnBr_2 in SbCl_3 solution exhibits the change in color only after 30 seconds of DMEDA injection, suggesting significantly lower reduction rate, consistent with the effect of these additives observed on CQD growth. Quantitative comparison of the SbCl_3 reduction with and without ZnX_2 is reported in Figure 1c. Notably, neat ZnBr_2 solution shows no change in color even after 24 hours of injection, suggesting that Zn remains inert against reacting with DMEDA (Figure S6).

Among various tested ZnX_2 salts under comparable synthesis conditions, CQD prepared using ZnBr_2 shows narrowest size distribution (Figure S7). Therefore, the discussion here onward is focused on InSb CQD prepared using ZnBr_2 as an additive.




Figure 2. ZnBr_2 assisted size-tuning of InSb CQDs. (a) Synthesis scheme. (b) Size dependent absorption spectra of the InSb CQD. (c) Optical absorption (Abs) and photoluminescence (PL) spectra of representative CQD dispersion. (d) high angle annular dark field scanning transmission electron microscopy images (HAADF-STEM) of InSb CQD reported in panel c. High-resolution transmission

electron microscopy (HRTEM) image of the CQD is reported as an inset in the same image and the size of the scale bars is 5 nm.

To tune the optical features of InSb CQD, we performed the entire synthesis under an oxygen-free environment using similar methods to those discussed above, which are illustrated in Figure 2a. The reaction time was varied from 10 to 45 min while keeping all other synthetic condition fixed. The optical spectroscopy analysis shows that under these conditions, the bandgap of the CQDs can be tuned from 960 nm to 1270 nm while retaining well-defined excitonic features in their absorption spectrum (Figure 2b). The corresponding emission tunes with the bandgap of the CQDs (Figure S8) and PL lifetimes increases as the CQD size increases, see Figure S9 for PL lifetime traces. Figure 2c, shows the well-defined excitonic absorption peak at 1165 nm of a representative sample which is subsequently used for ligand exchanges and devices. The steep absorption edge without a long tail is a sign of the highly monodisperse quantum dot ensemble, which we confirmed with HAADF-STEM (Figures 1-d and S7). The PL has a Stokes shift of 120 nm with a peak centered at 1286 nm. The PL spectrum has a FWHM of 136 nm. The PL quantum yield of this CQD batch in solution was 5 ± 2 %. We monitored the optical features of these materials over the a 9-week span and found there was no observable change (Figure S10-12).

We then turned to deploying these CQDs in the active layer in IR photodetectors. To create high-conductive CQD solids, we developed an in-solution ligand exchange process to remove the bulky, insulating aliphatic ligands for short halide ligands. This process was based on those developed for II-VI and other III-V CQD [18, 19] and is described in Figures 3a and S13. The synthesized InSb CQD were dispersed in hexane and added to a dimethylformamide (DMF) solution that contained the halide ligands. We found that that the DMF solution with just the metal halide ligands (InX_3) resulted in non-dispersible CQD solids. Using X-ray photoelectron spectroscopy (XPS) we found that the surface of the with metal halide CQD is In rich and therefore forming aggregates due to abundant non-coordinated metal on CQD surface.

We postulated that organic amino-halide ligand could reduce the metallic surface of CQDs. We used a mixture of tetrabutylammonium (TBA) and methylammonium (MA) halides in presence of acetic acid (AA) that enabled the exchanged CQD to be stable in the final solution (Figure 3a, b and S14). An exchange utilizing only TBA or InX_3 resulted in the incomplete removal of the oleate ligands (Figure 3e), resulting in colloiddally unstable ink (details in Methods). Addition of AA to the mixture provided acidic hydrogens that facilitated carboxylate removal and results in colloiddally stable ink.[20]




Figure 3: Ligand exchanges and photophysical characterization of the CQD: (a) Scheme of the ligand exchange processes. (b) photography of ligand exchanged samples. (c) PL decay traces of pristine and ligand exchanged CQD. (d) Transient absorption maps of pristine and ligand exchanged CQD after photoexcitation at 800 nm. (e) FTIR analysis of the CQD before exchanges, after TBAX, and mixture TBAX plus MAX exchanged treated samples.

Ultrafast pump-probe transient absorption (TA) and transient photoluminescence spectroscopy of pristine and ligand exchanged CQD (Figures 3c) were used to study the effect of ligand exchange on the InSb CQD charge carrier dynamics. These transient measurements are suggestive of a trap state

density increased following ligand exchange (Figure 3D). While the transient PL of the OA-capped CQD fit well to a single exponential, indicating charge carriers accumulate at the band edge for radiative recombination, the ligand-exchanged CQDs require a second component to the fit (Figure S15). With a double-exponential, the OA-capped and ligand-exchanged CQD exhibit a longer component of 90 and 100 ns, respectively, which we assign to radiative recombination. The second, shorter component (~ 9 ns), which we attribute to PL decay due to non-radiative recombination, was of larger magnitude for the ligand-exchanged sample. This increase of non-radiative recombination we connect with increased surface traps following the ligand exchange.

The transient absorption spectra, exhibiting bleaches within the steady-state absorbance peaks for both OA-capped and ligand-exchanged CQD, agree in trend with the carrier lifetimes and magnitudes observed using transient PL (Figure 3C). In particular, the bleach dynamics of the ligand-exchanged CQD were more complex than the bleach dynamics of the OA-capped CQD (Figure S15). Accounting for the band-edge recombination identified from transient PL, we identified two shorter components in the ligand exchanged bleach decay. The first, which was also found in the OA-capped CQD bleach, was of 1-2 ns and we link to non-radiative recombination. The second, which was not observed in the OA-capped CQD bleach, was significantly faster (46 ps). We tentatively attribute this fast component to multi-exciton generation (MEG) and fast Auger recombination (AR).[21] The appearance of MEG and AR further suggests an increase in trap state post ligand exchange. This increase in trap states is highlighted by the increase in magnitude of the two shorter bleach components relative to the OA-capped CQD.

Comparing FTIR spectra (Figure 3 e) of the CQD films before and after exchanges with TBAX reveals substantial decrease in C-H resonances around 2950 cm^{-1} indicating partial substitution of the native ligands. Contrary to this, the use of TBAX-MAX mixture shows complete removal of the organic ligands in the final ink. The presence of MAX in the ligands exchange solution shifts the equilibrium towards the displacement of organic ligands with halides, resulting in halide passivated CQD. This suggests a single step cascade resurfacing of CQD where acetic acid displace native carboxylate ligands, thereby shifting the equilibrium towards higher binding affinity to halide ligands in polar medium.[20, 22, 23] Furthermore, we found that the presence of acetic acid during ligand exchange significantly affects the stability of the final ink. The ligand exchanged samples prepared without using acetic acid resulted in CQD aggregation after one week of storage. Nevertheless, the ligand exchange sample prepared in presence of acetic acid remains stable after multiple cycles of washing and retain optical features upon storage. This is likely due to acetic acid assisted protonation of halide ligands which facilitates the colloidal stability of the ink.[24] The proposed ligand exchange mechanism is detailed in in Figure S14.

PXRD analysis of the CQD after ligand exchange shows phase pure zinc blend InSb CQD (Figure S16), indicating that the inorganic core of the CQD remains intact during resurfacing. XPS analysis of the pristine and ligand exchanged CQD shows significant decrease in the O1s peak, and reduction of the

InSb ($3d_{5/2}$) peak width (Figures S17-18), implying the clean CQD surface. Elemental analysis via XPS revealed that, upon exchange, the In:Sb ratio decreased from 2.1 to 1.6 indicating the removal of surface indium atoms. This observation is consistent with previous reports describing post ligand exchange reconstruction of III-V CQD surfaces.[18] A higher In/Sb ratio in the initial sample (before ligand exchanges) may result from indium halide-rich CQD surfaces and/or residual indium-organic complexes.




Figure 4: InSb CQD based IR photodetectors performance. (a, and b) Scheme showing the device architecture used in InSb photodetectors devices and the band alignment of layers. (c) Dark and illuminated J-V characteristics of InSb photodetector. The supplementary table 2 shows summary of dark current, current density, open circuit voltage and rectification ratio. (d) EQE (1 V) and (e) transient photocurrent and (f) detectivity of InSb CQD photodetector.

InSb photodetectors are fabricated using the structure of Figure 4a. ZnO nanoparticles are deposited on an ITO substrate, followed by the deposition of the ligand-exchanged InSb CQDs. Molybdenum oxide (MoOx) is then thermally evaporated onto the InSb CQD active layer. The structure is completed with Ag deposition to form the photodetector top contact. Previous studies on III-V CQDs photodetectors shows that using an Au electrode (instead of Ag) did not lead to improved performance, despite Au's deeper work function. [25, 26] This is likely due to better energy alignment between the Ag work function and the conducting intra-band states in MoOx. Additionally, due to its cost-effectiveness compared to Au, we opted to utilize Ag consistently in the present study. Alternative device structures were explored but resulted in poor diode behavior and

high dark currents (Figure S20 and supplementary Table 3). Future studies could seek to enhance band alignment and charge extraction mechanisms in InSb CQD devices.

Ultraviolet photoelectron spectroscopy (UPS) shows that valence band of ligand exchanged QD films shifted towards vacuum compared to the pristine CQD (Figure S21). The band alignment of the overall device architecture used in this study is reported in Figure 4b. Although the MoO₃ layer has an energy potential difference of ~0.15 eV with the valence band of the CQD active layer, it efficiently blocks electron back injection, successfully lowering the dark current compared to the control devices prepared without using MoO₃ blocking layer. This result in dark current of 0.48 mA/cm² at 1.0 V reverse bias (Figure 4 c).

The external quantum efficiency (EQE) of the InSb device presented in Figure 4d demonstrated a remarkable value of 74.4 % under 1 V bias. We then investigated the photodetector's transient photocurrent responses (Figure 4e). The photodetector shows a rise and fall times (from 10% to 90% and 90 % to 10 % of the normalized photocurrent) of 7.3 μ s and 5.4 μ s respectively. We measured a specific detectivity (based on noise current) of 10¹¹ Jones (5-50 kHz) at 1200 nm (Figure S23). We studied the stability of InSb CQD photodetector devices before and after encapsulation in ambient air. Non-encapsulated devices showed high instability under ambient conditions. UV-resin encapsulation improved stability, but prolonged exposure led to changes in JV characteristics—increased leakage, and smaller J_{sc} value due to oxidation of InSb CQDs. This suggests that the current UV-resin encapsulation method may not be entirely effective in safeguarding the devices and highlights the need for more effective encapsulation strategies due to the sensitiveness of the InSb CQDs to air.

In conclusion, we report here a synthetic strategy to prepare nearly monodisperse InSb CQD combining off-the-shelf non-pyrophoric precursors together with various zinc halides additives. Combined experimental and computational studies shows that ZnX₂ slows down the reduction of SbCl₃. The improved control over the antimony precursor during nucleation and growth enables the synthesis of monodisperse CQD. A post-synthetic surface treatment based on MAX:TBAX and acetic acid results in complete displacement of the native long chain organic ligands and the formation of CQD solids. This enabled us to fabricate a highly efficient InSb-based photodetector, achieving a detectivity of 1.02×10¹¹ Jones and EQE of 75% at 1200 nm, a record among all reported lead free CQD based photodetectors.

METHODS

Materials: Indium chloride (InCl₃, 99.99%), Oleic acid (OA, 99%), Oleylamine (OLA, 98%), N,N-Dimethylformamide (DMF, 99.8% anhydrous), Alane N,N-dimethylethylamine complex solution (DMEDA, 0.5 M Toluene), Zinc chloride (ZnCl₂, >98%), Zinc Bromide (ZnBr₂, 99.999%), octane

(99% anhydrous), Acetonitrile (ACN, 99.8% anhydrous), Toluene (Tol, 99.8% anhydrous), Methylammonium halides (MAX, 99%), Tetrabutylammonium halides (TBAX, 99%) were purchased from sigma. Indium (III) bromide (InBr_3 , 99.999% anhydrous) and Antimony(III) chloride (99%), were purchased from Strem Chemicals, Inc. Zinc fluoride (ZnF_2 , anhydrous) and Zinc iodide (ZnI_2 , 98%) were purchased from fisher scientific. All the mentioned chemicals were used as received.

InSb Colloidal Quantum Dot Synthesis: A solution mixture of 1 mmol of InCl_3 , 2.85 mmol of ZnX_2 and 35 mL of OLA was added in a 250 mL flask while stirring and kept under a vacuum at 120°C for 3h. After that, the reaction mixture is cool down to 50°C followed by a sequential injection of 1.3 mL SbCl_3 -OLAM (separately prepared by dissolving in 285 mg of SbCl_3 in 5 mL of pre-dried OLA) and 5 mL alane N,N-dimethylethylamine (5 mL). Subsequently, the reaction temperature is increased to 260°C and maintained for desired time (15-45 minutes). Then, the reaction flask is allowed to cool down to room temperature and CQDs are precipitated using acetonitrile as an antisolvent followed by their redispersion in toluene. Detailed steps for initial ligand exchanges and washing of CQDs are provided in the Supporting Information.

Control experiments for the reduction of SbCl_3 , with and without ZnX_2 , were conducted in a completely oxygen-free environment, employing methods similar to those used in the synthesis of CQDs.

Solution phase ligand exchanges: The solution phase ligand exchange process for InSb CQD was performed under ambient conditions. The pristine InSb CQD, with native OA ligands, were dispersed in an anhydrous hexane solvent with a concentration of $\sim 50\text{ mg/mL}$. A ligand exchange solution was prepared by dissolving a halide source compound in 5 mL of DMF in a molar ratio of 1:5(0.5):5:0.15, where each ratio represents $\text{MAI}:\text{TBABr}(\text{MABr}):\text{TBAI}:\text{AA}$, respectively. Note that AA ($\sim 10\text{ }\mu\text{L}$, 0.15 mmol) was added after dissolving all the halide compounds in DMF to prevent side reactions. Then 0.3-0.6 mL of OA-capped InSb CQD in hexane were vigorously mixed with 0.6-1.2 mL of the ligand exchange solution for 2 min using a vortex. Once the InSb CQD were transferred to the DMF phase, the transparent organic layer was removed, followed by adding 1 mL of fresh anhydrous hexane to the DMF phase for washing. This process was repeated twice to remove organic residue from the final ink. The halide capped InSb CQD in the DMF phase were precipitated by adding anhydrous toluene and hexane. The pellet was then redispersed in pure DMF and precipitated once more to remove any TBA or MA residual in the DMF phase. Finally, the precipitate was dried completely and redispersed in a DMF:ACN (1:3, v/v) solvent mixture with a concentration of $\sim 300\text{ mg/mL}$ to create an InSb CQD ink. The ink was centrifuged at 14,000 rpm for 2 min just before the film deposition process. We sought to simplify the materials processing protocol by removing one of the halide sources (either TBAX or MAX). This change resulted in 1) aggregation of CQDs at the interface of solvent mixture during the two-phase ligand exchange, and 2) less dispersible CQDs following the ligand exchange reaction. Similarly, the addition of InX_3 during ligand exchange reaction was found to be detrimental to ink stability of CQDs. In contrast, use of the mixture of TBAX and MAX results in

a stable ink. We believe that both have a role to play: MAX is a primary ammonium and thus more acidic, which has been shown to help with stripping off the original ligand. TBAX is more bulky, which may help with colloidal stability.

Device Fabrication: The ITO glass substrate was thoroughly cleaned using sonication with DI water, acetone, and isopropanol, each for 30 min. For the ZnO layer, pre-synthesized ZnO nanoparticles at a concentration of 80 mg/mL were spin-coated twice onto the substrate at 5000 rpm for 30 s. The active layer was deposited in the glove box on top of the ZnO layer using 35 μ L of InSb ink, utilizing a two-step spin-coating process consisting of 1000 rpm for 20 s followed by 1500 rpm for 30 s. Finally, the device was completed by thermal deposition of a 10 nm MoO₃ layer and a 140 nm silver electrode layer onto the active layer. All device measurements are done under ambient air at room temperature.

Characterization of CQD and devices:

FTIR Spectroscopy: The FTIR measurements were carried out using the Thermo Scientific iS50 instrument, covering the spectral range from 8000 to 350 cm^{-1} with a resolution of 4 cm^{-1} . The measurements were performed in attenuated total reflection (ATR) configuration.

Transient Absorption Measurements: The 5 kHz repetition rate femtosecond laser pulses were generated using a regeneratively amplified Yb:KGW laser (PHAROS, Light Conversion) with a 1030 nm fundamental wavelength. The fundamental was used to produce a pump beam at 400 nm with an optical parametric amplifier (ORPHEUS, Light Conversion). Then, the pump and fundamental were aligned into a commercial transient absorption spectrometer (Helios, Ultrafast). To generate the white continuum probe, the fundamental through a delay stage is focused into a sapphire crystal. The pump beam repetition rate is controlled by a mechanical chopper, reducing its repetition rate to 2.5 kHz. The TA measurements were performed using an average power of 1 μ W with a spot size of 0.4 μm^2 .

Device current-voltage Characterization: Keithley 2400 source meter is used for current-voltage measurements, scanned from -1 V to $+1$ V in 0.02 V steps without interval delay time.

Device response time measurement: The time response of the InSb device was measured using a 1-GHz oscilloscope (DSO8104A Infinium, Agilent). A 1310 nm diode laser (Thorlabs ML725B8F) connected to a function generator (Agilent 33220A) to modulate 10 kHz was used as an illumination source. The Femto DHPA-100 pre-amplifier at 10^3 V A⁻¹ was used for photodetector signal amplification.

PL Characterization. Steady-state PL was measured by a Horiba Fluorolog system with a monochromatized Xe lamp as the excitation source. To acquire transient PL, a time-correlated single photon counting (TCSPC) detector and a pulsed NIR laser diode (DD-830L, DeltaDiode, 820 nm,

HORIBA Scientific) were used. The sample was illuminated 15° with respect to the surface normal. The photoluminescence was collected at 75° with respect to the surface normal and measured with a iHR320 spectrometer (HORIBA Scientific, 600 grooves/mm, 1000 nm blaze wavelength) and InGaAs photodetector (S1-H10330-75).

PL QY measurements. The measurements were performed by using a Quanta-Phi integrating sphere of the Fluorolog system. Prior to the measurements, the detector was calibrated for spectral variance with a Newport white light source to ensure accurate values.

TA measurements. A regeneratively amplified Yb:KGW laser (PHAROS, Light Conversion) was used to generate femtosecond laser pulses (1030 nm, 5 KHz repetition rate, ~ 200 fs). The majority of the beam power was used to pump an optical parametric amplifier (ORPHEUS, Light Conversion) to generate the pump laser (FWHM ~ 10 nm) which was passed through a chopper (pump repetition = 2.5 KHz). The remaining portion of the 1030 nm beam was passed through a delay stage and focused through a sapphire crystal to generate a white light continuum probe in the NIR. The pump and probe beams were focused spatially and temporally through the sample at an angle of $\sim 30^\circ$ with respect to each other. The remaining probe light was directed into a commercial transient absorption spectrometer (Helios, Ultrafast Systems, InGaAs 256 pixels). Sample measurement was obtained with a pump power of 1000 μ W.

PXRD Measurements. PXRD measurements were conducted using a Rigaku MiniFlex 600 diffractometer (Bragg-Brentano geometry) equipped with a NaI scintillation counter detector and a monochromatized Cu K α radiation source ($\lambda = 1.5406$ Å) operating at a voltage of 40 kV and current of 15 mA.

Transmission Electron Microscopy (TEM) Characterization. Bright-field TEM, high-resolution TEM, and scanning transmission electron microscopy high-angle annular dark-field (STEM-HAADF) images of the QD samples were acquired using a Hitachi HF-3300 transmission electron microscope operating at an accelerating voltage of 300 kV. The samples were prepared by drop casting diluted solutions of NCs onto carbon-coated 200 mesh copper grids.

High-Resolution TEM and Energy Dispersive X-ray Spectroscopy. The characterization was performed by using a JEOL JEM2200 image-corrected instrument operated at 200 kV and equipped with an in-column Omega energy filter and Bruker Quantax 400 EDX system with a 60 mm² XFlash detector. Partial HRTEM and EDS characterization were taken on a ThermoFisher Scientific Titan Cubed Themis G2 300 transmission electron microscope with an acceleration voltage of 300 kV and equipped with a Super-X4 probe super energy spectrum.

External Quantum Efficiency Measurement: The EQE of InSb devices were measured with EnlinTech QE-R Quantum Efficiency Analyzer, 400-1700 nm, resolution 10 nm, monochromatic light chopped mechanically in 210 Hz.

DFT calculations: Calculations have been performed in CP2K suite[27], using Goedecker-Tetter Hutter pseudopotentials[28], generalized gradient approximation with Perdew-Burke-Ernzerhoff functional [29], and DZVP basis set optimized for molecules [30].

Methylamine was used instead of oleylamine to minimize the number of atoms in simulations and minimize the degrees of freedom to avoid energy fluctuations. Similarly, dimethylethylamine on the alane was replaced by the methylamine, anticipating an easy exchange of the amine ligand in the neat amine solvent solution. Molecular dynamics simulations were performed to test how metal halides dissolve in amines and then representative geometries were used in Sb-halide-alane interactions. We find that the precursors in OLA do not dissociate into ions (Sb^{3+} , Zn^{2+} , Cl^-) completely and cations remain coordinated to halides. A loss or gain of one halide ion is in principle possible, resulting in charged complexes, e.g. SbCl_4^- and ZnCl^+ , in addition to the more abundant SbCl_3 and ZnCl_2 coordinated by amines.

Configurations with 2, 3, 4 halides around Sb, as well as with full ZnCl_2 molecule attached to SbCl_3 all failed to explain the reduction process by AlH_3 . Even though without the explicit solvent it was possible to block the reduction, the energetics of the reaction would completely change when explicit amines were included. In addition, amine hydrogens would coordinate to the halide and further facilitate barrierless transfer of H from Al to Sb, and Cl from Sb to Al.

Supporting Information

Supporting Information is available from the Wiley Online Library or from the author.

Acknowledgements

The authors also thank Dr. Amin M. Najarian, Larissa Levina, Elenita Palmiano, Remi Wolowiec, and Damir Kopilovic for their assistance during the period of study.

Conflict of Interest

The authors declare no conflict of interest.

Received: ((will be filled in by the editorial staff))
Revised: ((will be filled in by the editorial staff))
Published online: ((will be filled in by the editorial staff))

References

This article is protected by copyright. All rights reserved.

1. García de Arquer, F.P., et al., *Semiconductor quantum dots: Technological progress and future challenges*. Science, 2021. **373**(6555): p. eaaz8541.
2. Rogalski, A., et al., *InAsSb-based infrared photodetectors: Thirty years later on*. Sensors, 2020. **20**(24): p. 7047.
3. Xiao, X., et al., *High quality silicon: colloidal quantum dot heterojunction based infrared photodetector*. Applied Physics Letters, 2020. **116**(10): p. 101102.
4. Neathery, M. and W. Miller, *Metabolism and toxicity of cadmium, mercury, and lead in animals: a review*. Journal of dairy science, 1975. **58**(12): p. 1767-1781.
5. Kim, T., et al., *Development of Group III–V Colloidal Quantum Dots for Optoelectronic Applications*. ACS Energy Letters, 2022. **8**: p. 447-456.
6. Liu, W., et al., *Colloidal insb nanocrystals*. Journal of the American Chemical Society, 2012. **134**(50): p. 20258-20261.
7. Srivastava, V., et al., *Monodisperse InAs quantum dots from aminoarsine precursors: understanding the role of reducing agent*. Chemistry of Materials, 2018. **30**(11): p. 3623-3627.
8. Busatto, S., et al., *Luminescent colloidal InSb quantum dots from In situ generated single-source precursor*. ACS nano, 2020. **14**(10): p. 13146-13160.
9. Zhao, T., et al., *General synthetic route to high-quality colloidal III–V semiconductor quantum dots based on pnictogen chlorides*. Journal of the American Chemical Society, 2019. **141**(38): p. 15145-15152.
10. Ginterseder, M., et al., *Scalable synthesis of InAs quantum dots mediated through indium redox chemistry*. Journal of the American Chemical Society, 2020. **142**(9): p. 4088-4092.
11. Ghosh, S. and L. Manna, *The many “facets” of halide ions in the chemistry of colloidal inorganic nanocrystals*. Chemical reviews, 2018. **118**(16): p. 7804-7864.
12. Li, H., et al., *ZnF₂-assisted synthesis of highly luminescent InP/ZnSe/ZnS quantum dots for efficient and stable electroluminescence*. Nano Letters, 2022. **22**(10): p. 4067-4073.
13. Song, W.-S., et al., *Amine-derived synthetic approach to color-tunable InP/ZnS quantum dots with high fluorescent qualities*. Journal of nanoparticle research, 2013. **15**: p. 1-10.
14. Calvin, J.J., et al., *Thermodynamic investigation of increased luminescence in indium phosphide quantum dots by treatment with metal halide salts*. Journal of the American Chemical Society, 2020. **142**(44): p. 18897-18906.
15. Grigel, V., et al., *InAs colloidal quantum dots synthesis via aminopnictogen precursor chemistry*. Journal of the American Chemical Society, 2016. **138**(41): p. 13485-13488.

16. Tietze, R., et al., *Synthesis of NIR - Emitting InAs - Based Core/Shell Quantum Dots with the Use of Tripyrazolylarsane as Arsenic Precursor*. Particle & Particle Systems Characterization, 2018. **35**(9): p. 1800175.
17. Zhu, D., et al., *ZnCl₂ Mediated Synthesis of InAs Nanocrystals with Aminoarsine*. Journal of the American Chemical Society, 2022. **144**(23): p. 10515-10523.
18. Choi, M.-J., et al., *Ligand exchange at a covalent surface enables balanced stoichiometry in III–V colloidal quantum dots*. Nano letters, 2021. **21**(14): p. 6057-6063.
19. Yang, Z., et al., *Mixed-quantum-dot solar cells*. Nature communications, 2017. **8**(1): p. 1325.
20. Balazs, D.M., et al., *Counterion-mediated ligand exchange for PbS colloidal quantum dot superlattices*. ACS nano, 2015. **9**(12): p. 11951-11959.
21. Chang, A.Y., et al., *Carrier dynamics in highly quantum-confined, colloidal indium antimonide nanocrystals*. ACS nano, 2014. **8**(8): p. 8513-8519.
22. Choi, M.-J., et al., *Cascade surface modification of colloidal quantum dot inks enables efficient bulk homojunction photovoltaics*. Nature communications, 2020. **11**(1): p. 103.
23. You, H., W. Wang, and S. Yang, *A universal rule for organic ligand exchange*. ACS Applied Materials & Interfaces, 2014. **6**(21): p. 19035-19040.
24. Owen, J., *The coordination chemistry of nanocrystal surfaces*. Science, 2015. **347**(6222): p. 615-616.
25. Sun, B., et al., *Fast Near - Infrared Photodetection Using III -V Colloidal Quantum Dots*. Advanced Materials, 2022. **34**(33): p. 2203039.
26. Xia, P., et al., *Sequential Co - Passivation in InAs Colloidal Quantum Dot Solids Enables Efficient Near - Infrared Photodetectors*. Advanced Materials, 2023. **35**(28): p. 2301842.
27. VandeVondele, J., et al., *Quickstep: Fast and accurate density functional calculations using a mixed Gaussian and plane waves approach*. Computer Physics Communications, 2005. **167**(2): p. 103-128.
28. Goedecker, S., M. Teter, and J. Hutter, *Separable dual-space Gaussian pseudopotentials*. Physical Review B, 1996. **54**(3): p. 1703.
29. Perdew, J.P., K. Burke, and M. Ernzerhof, *Generalized gradient approximation made simple*. Physical review letters, 1996. **77**(18): p. 3865.
30. VandeVondele, J. and J. Hutter, *Gaussian basis sets for accurate calculations on molecular systems in gas and condensed phases*. The Journal of chemical physics, 2007. **127**(11).

InSb colloidal quantum dots (CQDs) show promise for extended infrared light sensing applications but face synthesis challenges due to uncontrolled reduction of precursors. Herein, we achieve the controlled growth of CQDs with well-defined excitonic transitions using zinc halide additives. The photodetectors employing ligand-exchanged CQDs achieve a 75% external quantum efficiency at 1200 nm with 1V applied bias.

